

# VT-901

UL Approval: E214381 Version: B7 /40 /41

## Laminate/Prepreg

### General Information

- > Tg 250°C
- > High Td
- > Improved Fracture Toughness
- > Low Z-axis CTE
- > Meets NASA requirements for no visible bromine

### Application

- > Chip Manufacturers
- > Engine/Flight Controls
- > Power Supply/Backplane
- > Military and Burn-in Board

### Availability

- > Core Thickness: 0.002" (0.05mm) to 0.125" (3mm), available in sheet or panel form
- > Copper Foil: 1/4oz to 6oz
- > Prepregs are available in roll or panel form
- > E-Glass styles: 7628, 1506, 2113, 2313, 3313, 2116, 1080, 106 etc

**Note:** Double side treated copper foil and reverse copper foil are not suggested using on VT-901 laminates because the peel strength would not be as good as conventional materials.

Properties		Prepreg		Laminate
Storage Condition	Temperature	Below 23°C (73°F)	Below 5°C (41°F)	Room
	Relative humidity	Below 55% RH	/	/
Shelf Life		3 months	6 months	24 months (airproof)

The prepreg exceeding shelf life should be retested.

#### CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.  
308 TaiShan Rd,  
New District Suzhou,  
Jiangsu, P.R. China 215129  
T: +86 512-68091810  
Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

Ventec Europe  
Unit 1 Trojan Business Centre,  
Tachbrook Park Estate,  
Leamington-Spa, CV34 6RH, UK  
T: +44 1926-889822  
Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

Ventec USA  
21 Water Street, Amesbury,  
Massachusetts, MA 01913,  
United States of America  
T: +1 978-5219700  
Email: saleseast@ventec-usa.com

www.ventecclaminates.com

# VT-901

## Laminate/Prepreg

UL Approval: E214381 Version: B6 /40 /41

### Properties Sheet IPC-4101E /40 /41

Properties		Test Method	Units	Specification	Typical Value
<b>Thermal Properties</b>					
Tg	DSC	IPC-TM-650 2.4.25	°C	–	–
	TMA	IPC-TM-650 2.4.24	°C	200 minimum	250
Td		ASTM D3850	°C	–	395
T260		IPC-TM-650 2.4.24.1	Minute	–	>60
T288		IPC-TM-650 2.4.24.1	Minute	–	>60
Thermal Stress @ 288°C		IPC-TM-650 2.4.13.1	Second	Pass 10s	>1200
Z-axis CTE	Before Tg	IPC-TM-650 2.4.24	ppm/°C	–	50
	After Tg	IPC-TM-650 2.4.24	ppm/°C	–	150
	Total Expansion (50~260°C)	IPC-TM-650 2.4.24	%	–	1.4
X-Y CTE		IPC-TM-650 2.4.24	ppm/°C	–	11~12
MOT		UL 94	°C	–	140
<b>Electrical Properties</b>					
DK @ 1GHz RC 40%		IPC-TM-650 2.5.5.9	–	5.4 maximum	4.05
DF @ 1GHz RC 40%		IPC-TM-650 2.5.5.9	–	0.035 minimum	0.012
Volume Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+8
	E-24/125	IPC-TM-650 2.5.17.1	MΩ-cm	1.0E+6 minimum	5.0E+6
Surface Resistivity	After Moisture Resistance	IPC-TM-650 2.5.17.1	MΩ	1.0E+6 minimum	5.0E+7
	E-24/125	IPC-TM-650 2.5.17.1	MΩ	1.0E+6 minimum	5.0E+6
Electrical Strength		IPC-TM-650 2.5.6.2	Volt/mil (KV/mm)	762 (30) minimum	1200~1400 (54)
Dielectric Breakdown		IPC-TM-650 2.5.6	KV	40 minimum	60
Comparative Tracking Index (CTI)		ASTM D3638	Rating (Volt)	–	Grade 4 (100~175)
Arc Resistance		ASTM D495	Second	120 minimum	150
<b>Mechanical Properties</b>					
Peel Strength (1oz)	As received	IPC-TM-650 2.4.8	lb/in (N/mm)	–	6~9 (1.05~1.58)
	After thermal stress	IPC-TM-650 2.4.8	lb/in (N/mm)	5.14 (0.90) minimum	6~9 (1.05~1.58)
Flexural Strength	Warp	IPC-TM-650 2.4.4	Kpsi (MPa)	60 (415) minimum	600 (87)
	Fill	IPC-TM-650 2.4.4	Kpsi (MPa)	47 (325) minimum	500 (72)
<b>Physical Properties</b>					
Moisture Absorption		IPC-TM-650 2.6.2.1	%	1.0 maximum	0.2
Flammability		UL-94	Rating	HB minimum	V0

Note: All test data provided are typical values and are not intended to be specification values.

#### CORPORATE HEADQUARTERS

Ventec Electronics Co. Ltd.  
 308 TaiShan Rd,  
 New District Suzhou,  
 Jiangsu, P.R. China 215129  
 T: +86 512-68091810  
 Email: sales@ventec.com.cn

#### EMEA REGIONAL HEADQUARTERS

Ventec Europe  
 Unit 1 Trojan Business Centre,  
 Tachbrook Park Estate,  
 Leamington-Spa, CV34 6RH, UK  
 T: +44 1926-889822  
 Email: sales@ventec-europe.com

#### AMERICAS REGIONAL HEADQUARTERS

Ventec USA  
 21 Water Street, Amesbury,  
 Massachusetts, MA 01913,  
 United States of America  
 T: +1 978-5219700  
 Email: saleseast@ventec-usa.com

www.ventec laminates.com